British Polythene Limited
t/a Visqueen Building Products
Heanor Gate
Heanor
Derbyshire DE75 7RG

Tel: 0845 302 4758 Fax: 0845 017 8663
e-mail: enquiries@visqueenbuilding.co.uk
website: www.visqueenbuilding.co.uk

Agrément Certificate
94/3059
Product Sheet 1

ZEDEX HIGH PERFORMANCE DAMP-PROOFING SYSTEM

ZEDEX CPT HIGH PERFORMANCE DAMP-PROOF COURSE

This Agrément Certificate Product Sheet(1) relates to Zedex CPT High Performance Damp-proof Course, a flexible sheet material manufactured from a mixture of thermoplastic polymers and additives, used to provide a horizontal, vertical or stepped damp-proof course (dpc) in either solid or cavity masonry walls.

(1) Hereinafter referred to as 'Certificate'.

CERTIFICATION INCLUDES:

- factors relating to compliance with Building Regulations where applicable
- factors relating to additional non-regulatory information where applicable
- independently verified technical specification
- assessment criteria and technical investigations
- design considerations
- installation guidance
- regular surveillance of production
- formal three-yearly review.

KEY FACTORS ASSESSED

Behaviour under load — the product will not extrude under load, and will not adversely affect the ability of a properly designed and built wall to sustain and transmit compression (see section 6).
Resistance to water and water vapour — the product will provide an effective barrier against moisture (see section 7).
Resistance to radon — the product will restrict the ingress of radon into the building (see section 8).
Compatibility with other materials — within normal construction, the product is compatible with all materials with which it will be in contact (see section 9).
Durability — when properly specified and installed, the product, in normal circumstances, will remain effective during the lifetime of the building (see section 11).

The BBA has awarded this Certificate to the company named above for the product described herein. This product has been assessed by the BBA as being fit for its intended use provided it is installed, used and maintained as set out in this Certificate.

On behalf of the British Board of Agrément

Date of Sixth issue: 23 July 2018

Originally certificated on 26 October 1994

John Albon – Head of Approvals Construction Products

Claire Curtis-Thomas
Chief Executive

Regulations

In the opinion of the BBA, Zedex CPT High Performance Damp-proof Course, if installed, used and maintained in accordance with this Certificate, can satisfy or contribute to satisfying the relevant requirements of the following Building Regulations (the presence of a UK map indicates that the subject is related to the Building Regulations in the region or regions of the UK depicted):



The Building Regulations 2010 (England and Wales) (as amended)

Requirement:	**A1**	**Loading**
Comment:		The product will not extrude under load up to the point of failure of the wall, and will not adversely affect the ability of a properly designed and built wall to sustain and transmit compression loads. See section 6.1 of this Certificate.
Requirement:	**C1(2)**	**Site preparation and resistance to contaminants**
Comment:		The product can contribute to satisfying this Requirement. See section 8.1 of this Certificate.
Requirement:	**C2(a)(b)**	**Resistance to moisture**
Comment:		Properly installed in a correctly designed structure, the product forms an effective barrier to the movement of water within the wall, enabling compliance with this Requirement. See section 7 of this Certificate.
Regulation:	**7**	**Materials and workmanship**
Comment:		The product is acceptable. See section 11 and the *Installation* part of this Certificate.

The Building (Scotland) Regulations 2004 (as amended)

Regulation:	**8(1)**	**Durability, workmanship and fitness of materials**
Comment:		The use of the product satisfies the requirements of this Regulation. See section 11 and the *Installation* part of this Certificate.
Regulation:	**9**	**Building standards applicable to construction**
Standard:	1.1(a)(b)	Structure
Comment:		The product will not extrude under load up to the point of failure of the wall, and will not adversely affect the ability of a properly designed and built wall to sustain and transmit compression loads, with reference to clauses 1.1.1$^{(1)(2)}$ and 3.10.1$^{(1)(2)}$ of this Standard. See section 6.1 of this Certificate.
Standard:	3.1	Site preparation – harmful and dangerous substances
Standard:	3.2	Site preparation – protection from radon gas
Comment:		The product can contribute to satisfying the requirements of these Standards, with reference to clauses 3.1.6$^{(1)(2)}$, 3.2.0$^{(1)(2)}$, 3.2.1$^{(2)}$ and 3.2.2$^{(1)}$. See section 8.1 of this Certificate.
Standard:	3.4	Moisture from the ground
Comment:		Properly installed in a correctly designed structure, the product will form an effective barrier to the movement of water within the wall, enabling compliance with this Standard, with reference to clause 3.4.1$^{(1)(2)}$. See section 7 of this Certificate.
Standard:	7.1(a)	Statement of sustainability
Comment:		The product can contribute to meeting the relevant Requirements of Regulation 9, Standards 1 to 6 and therefore will contribute to a construction meeting a bronze level of sustainability as defined in this Standard.

Regulation:	**12**	**Building standards applicable to conversions**
Comment:		Comments in relation to the product under Regulation 9, Standards 1 to 6 also apply to this Regulation, with reference to clause 0.12.1[(1)(2)] and Schedule 6[(1)(2)]. (1) Technical Handbook (Domestic). (2) Technical Handbook (Non-Domestic).

The Building Regulations (Northern Ireland) 2012 (as amended)

Regulation:	**23(a)(i) (iii)(b)(i)**	**Fitness of materials and workmanship**
Comment:		The product is acceptable. See section 11 and the *Installation* part of this Certificate.
Regulation:	**26**	**Site preparation and resistance to contaminants**
Comment:		When properly installed in a correctly designed structure, the product forms an effective barrier to radon, enabling compliance with this Requirement. See section 7 of this Certificate.
Regulation:	**28(a)(b)**	**Resistance to moisture and weather**
Comment:		Properly installed in a correctly designed structure, the product forms an effective barrier to the movement of water within the wall, enabling compliance with this Regulation. See section 8.1 of this Certificate.
Regulation:	**30**	**Stability**
Comment:		The product will not extrude under load up to the point of failure of the wall, and will not adversely affect the ability of a properly designed and built wall to sustain and transmit compression loads. See section 6.1 of this Certificate.

Construction (Design and Management) Regulations 2015
Construction (Design and Management) Regulations (Northern Ireland) 2016

Information in this Certificate may assist the client, designer (including Principal Designer) and contractor (including Principal Contractor) to address their obligations under these Regulations.

See section: 1 *Description* (1.2) of this Certificate.

Additional Information

NHBC Standards 2018

In the opinion of the BBA, Zedex CPT High Performance Damp-proof Course, if installed, used and maintained in accordance with this Certificate, can satisfy or contribute to satisfying the relevant requirements in relation to *NHBC Standards*, Chapter 6.1 External masonry walls.

CE marking

The Certificate holder has taken the responsibility of CE marking the product, in accordance with harmonised European Standard BS EN 14909 : 2012. An asterisk (*) appearing in this Certificate indicates that data shown are given in the manufacturer's Declaration of Performance.

Technical Specification

1 Description

1.1 Zedex CPT High Performance Damp-proof Course is a flexible sheet comprising a mixture of thermoplastic polymers and other additives, extruded into sheet form, reeled into rolls and cut to width.

1.2 The product has the nominal characteristics given in Table 1.

Table 1 Nominal characteristics

Characteristic (unit)	Value
Thickness (mm)	0.8
Mass ($g \cdot m^{-2}$)	750
Roll length (m)	20
Roll width (mm)(1)	100 to 1400
Watertightness (2 kPa)	Pass
Durability (artificial ageing)	Pass
Durability (alkali)	Pass
Resistance to low temperature (°C)	-40
Resistance to impact (mm)	350
Resistance to static loading (kg)	20
Colour	black

1.3 Also for use with the product and included in this assessment is Visqueen Zedex DPC Jointing Tape.

2 Manufacture

2.1 The product is manufactured from a blend of thermoplastic polymers and extruded into sheet form.

2.2 As part of the assessment and ongoing surveillance of product quality, the BBA has:

- agreed with the manufacturer the quality control procedures and product testing to be undertaken
- assessed and agreed the quality control operated over batches of incoming materials
- monitored the production process and verified that it is in accordance with the documented process
- evaluated the process for management of nonconformities
- checked that equipment has been properly tested and calibrated
- undertaken to carry out the above measures on a regular basis through a surveillance process, to verify that the specifications and quality control operated by the manufacturer are being maintained.

2.3 The management system of British Polythene Limited t/a Visqueen Building Products has been assessed and registered as meeting the requirements of BS EN ISO 9001 : 2015 by Knights International Inspectorate (Certificate 4560).

3 Delivery and site handling

3.1 The product is delivered to site in rolls secured with a wrapper bearing the manufacturer's name and the BBA logo incorporating the number of this Certificate.

3.2 Rolls must be stored on end and under cover.

Assessment and Technical Investigations

The following is a summary of the assessment and technical investigations carried out on Zedex CPT High Performance Damp-proof Course.

Design Considerations

4 Use

4.1 Zedex CPT High Performance Damp-proof Course, when correctly specified and installed in accordance with this Certificate, is satisfactory for use as a horizontal, vertical, or stepped dpc (including cavity trays) in either solid or cavity walls of brick, block, stone or concrete.

4.2 General standards of good design practice are given in BS EN 1996-1-1 : 2005, BS EN 1996-2 : 2006 and BS EN 1996-3 : 2006 and their UK National Annexes, and PD 6697 : 2010.

4.3 The product may be used in conjunction with beam and block flooring.

4.4 The product must be used in conjunction with a gas-resistant membrane to restrict the ingress of radon into buildings. Buildings in areas of risk should be constructed in accordance with the recommendations of BRE Report BR 211 : 2015 and following the guidance set out in BS 8485 : 2015.

5 Practicability of installation

The product should be installed by bricklayers experienced with this type of product.

6 Behaviour under load

6.1 The product will not extrude under load up to the point of compressive failure of the wall, and will not adversely affect the ability of a properly designed and built wall to sustain and transmit compression load.

6.2 The stability of a wall in respect of lateral loads must be checked in relation to the stresses permitted between the dpc and the mortar. A wall incorporating the product must be designed and built in accordance with BS EN 1996 -1-1 : 2005.

6.3 The product will withstand movement of the wall and is unlikely to be impaired by normally occurring movements up to the point where the wall itself is deemed to have failed.

6.4 The presence of a dpc can reduce the shear and tensile (and therefore, bending) strengths of a wall at that point, and design of the structure should take account of this. Shear tests carried out to BS EN 1052-4 : 2000 at a pre-compression load of 0.2, 0.6 and 1 $N \cdot mm^{-2}$ gave a characteristic shear strength as detailed in Table 2. The characteristic flexural strength as tested to DD 86-1 : 1986 is 0.17 $N \cdot mm^{-2}$.

Table 2 Characteristic shear strength of Zedex CPT High Performance Damp-proof Course

Pre-compression ($N \cdot mm^{-2}$)	Characteristic shear strength ($N \cdot mm^{-2}$)
0.2	0.25
0.6	0.37
1	0.48

7 Resistance to water and water vapour

When correctly specified and installed, the product will provide an effective barrier against liquid water and water vapour either from a source external to the structure or from one part of the structure to another.

8 Resistance to radon

8.1 The product will restrict the ingress of radon into buildings from naturally occurring sources.

8.2 Measured gas permeability/diffusion values on an unjointed membrane are given in Table 3.

Table 3 Gas permeability/diffusion values

Gas	Method	Result
Radon	SP Method No. 3873	8.3×10^{-12} $m^2 \cdot s^{-1}$

9 Compatibility with other materials

The product is compatible with most materials with which it is likely to come into contact within normal construction, including timber preservatives of water-based solutions of salts.

10 Maintenance

As the product is confined within the wall cavity and has suitable durability (see section 11), maintenance is not required.

11 Durability

When properly specified and installed, the product, in normal circumstances, will remain effective for the lifetime of the building.

Installation

12 General

12.1 Installation of Zedex CPT High Performance Damp-proof Course must be in accordance with the Certificate holder's instructions, the relevant clauses of PD 6697 : 2010, BS 8000-3 : 2001 and BS 8215 : 1991, BRE Digest 380 and BRE Report BR 211 : 2015.

12.2 As with all flexible dpcs, care should be taken to avoid impact damage from sharp objects (eg chisels) during installation.

12.3 The product is handled in the same manner as that for conventional flexible dpcs, and is cut with a sharp knife. It will remain sufficiently flexible for installation in low temperatures and will not become tacky in warm conditions.

12.4 The continuity of the gas protection must extend over the footprint of the building and the dpc must be sealed to a gas membrane.

13 Procedure

13.1 The product must be laid on a wet, even bed of mortar and extend through the full thickness of the wall or wall leaf, including pointing, applied rendering or other facing material.

13.2 Perforations in adjacent courses of brickwork must be completely filled with mortar.

13.3 All lap joints in the dpc must have a minimum 100 mm overlap, be completely sealed with Visqueen Zedex DPC Jointing Tape and be supported by a suitable joint system in accordance with the Certificate holder's instructions.

13.4 When using the product with boot lintels or similar constructions, it is installed to follow the lintel profile wherever possible.

13.5 As with other similar materials, care must be taken to avoid damaging the dpc during cleaning of mortar droppings. Recommendations for avoiding damage occurring are:

- use of cavity battens to prevent mortar droppings from reaching the dpc
- removal of mortar droppings before they harden
- avoidance of the use of implements such as steel rods for cleaning the cavity
- inspection of cavity trays for damage as work proceeds.

Beam and block flooring

13.6 When used with beam and block flooring, the dpc may be laid dry on a brick or block wall provided that:

- minimum bearing(1) of the beam is achieved
- dead and applied loads upon the dpc via the beam do not exceed 2.5 $N \cdot mm^{-2}$
- the surface of the wall onto which the dpc and beam are to be installed is clean, smooth and free from projections or perforations. If this cannot be achieved, the dpc should be laid in an even bed of mortar
- loose aggregate is swept from the wall prior to installation of the dpc, and from the dpc prior to installation of the beams.

(1) As recommended by the flooring manufacturer.

14 Repair

Damaged areas of the product can be repaired prior to installation, by cutting and/or replacing the damaged section, ensuring that joints are made in accordance with section 13.3. Once covered, the product cannot be repaired.

Technical Investigations

15 Tests

Tests were carried out and the results assessed to determine:

- weight
- water vapour permeability
- water vapour resistance
- water absorption
- resistance to water pressure
- resistance to impact
- tensile strength and elongation
- low temperature flexibility
- trouser tear
- nail tear
- dimensional stability
- heat ageing followed by tensile strength, elongation and low temperature flexibility
- water soak followed by tensile strength, elongation and low temperature flexibility.

16 Investigations

16.1 The manufacturing process was evaluated, including the methods adopted for quality control, and details were obtained of the quality and composition of the materials used.

16.2 An assessment was made of reports of shear and flexure tests.

16.3 An assessment was made of the compatibility of the product with chemicals with which it is likely to come in contact.

Bibliography

BRE Digest 380 *Damp-proof courses*

BRE Report BR 211: 2015 *Radon : protective measures for buildings*

BS 8000-3 : 2001 *Workmanship on building sites — Code of practice for masonry*

BS 8215 : 1991 *Code of practice for design and installation of damp-proof courses in masonry construction*

BS 8485 : 2015 *Code of practice for the design of protective measures for methane and carbon dioxide ground gases for new buildings*

BS EN 1052-4 : 2000 *Methods of tests for masonry — Determination of shear strength including damp proof course*

BS EN 1996-1-1 : 2005 + A1 : 2012 *Eurocode 6 — Design of masonry structures — General rules for reinforced and unreinforced masonry structures*
NA to BS EN 1996-1-1 : 2005 + A1 : 2012 UK National Annex to *Eurocode 6 — Design of masonry structures — General rules for reinforced and unreinforced masonry structures*
BS EN 1996-2 : 2006 *Eurocode 6 — Design of masonry structures — Design considerations, selection of materials and execution of masonry*
NA to BS EN 1996-2 : 2006 UK National Annex to *Eurocode 6 — Design of masonry structures —Design considerations, selection of materials and execution of masonry*
BS EN 1996-3 : 2006 *Eurocode 6 — Design of masonry structures — Simplified calculation methods for unreinforced masonry structure*
NA to BS EN 1996-3 : 2006 UK National Annex to *Eurocode 6 — Design of masonry structures — Simplified calculation methods for unreinforced masonry structures*

BS EN 14909 : 2012 *Flexible sheets for waterproofing — Plastic and rubber damp proof courses — Definitions and characteristics*

BS EN ISO 9001 : 2015 *Quality management systems — Requirements*

DD 86-1 : 1986 *Damp-proof courses — Methods of test for flexural bond strength and short term shear strength*

PD 6697 : 2010 *Recommendations for the design of masonry structures to BS EN 1996-1-1 and BS EN 1996-2*

17 Conditions

17.1 This Certificate:

- relates only to the product/system that is named and described on the front page
- is issued only to the company, firm, organisation or person named on the front page – no other company, firm, organisation or person may hold claim that this Certificate has been issued to them
- is valid only within the UK
- has to be read, considered and used as a whole document – it may be misleading and will be incomplete to be selective
- is copyright of the BBA
- is subject to English Law.

17.2 Publications, documents, specifications, legislation, regulations, standards and the like referenced in this Certificate are those that were current and/or deemed relevant by the BBA at the date of issue or reissue of this Certificate.

17.3 This Certificate will remain valid for an unlimited period provided that the product/system and its manufacture and/or fabrication, including all related and relevant parts and processes thereof:

- are maintained at or above the levels which have been assessed and found to be satisfactory by the BBA
- continue to be checked as and when deemed appropriate by the BBA under arrangements that it will determine
- are reviewed by the BBA as and when it considers appropriate.

17.4 The BBA has used due skill, care and diligence in preparing this Certificate, but no warranty is provided.

17.5 In issuing this Certificate the BBA is not responsible and is excluded from any liability to any company, firm, organisation or person, for any matters arising directly or indirectly from:

- the presence or absence of any patent, intellectual property or similar rights subsisting in the product/system or any other product/system
- the right of the Certificate holder to manufacture, supply, install, maintain or market the product/system
- actual installations of the product/system, including their nature, design, methods, performance, workmanship and maintenance
- any works and constructions in which the product/system is installed, including their nature, design, methods, performance, workmanship and maintenance
- any loss or damage, including personal injury, howsoever caused by the product/system, including its manufacture, supply, installation, use, maintenance and removal
- any claims by the manufacturer relating to CE marking.

17.6 Any information relating to the manufacture, supply, installation, use, maintenance and removal of this product/system which is contained or referred to in this Certificate is the minimum required to be met when the product/system is manufactured, supplied, installed, used, maintained and removed. It does not purport in any way to restate the requirements of the Health and Safety at Work etc. Act 1974, or of any other statutory, common law or other duty which may exist at the date of issue or reissue of this Certificate; nor is conformity with such information to be taken as satisfying the requirements of the 1974 Act or of any statutory, common law or other duty of care.